

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 60-156745

(43)Date of publication of application : 16.08.1985

(51)Int.Cl.

C08L 65/00

(21)Application number : 59-012002

(71)Applicant : ASAHI GLASS CO LTD

(22)Date of filing : 27.01.1984


(72)Inventor : KAWAHARA HIROSHI
OTSUKA IWAHIRO
KAYAME KIYOTERU
YAMADA YUTAKA

(54) ELECTRICALLY-CONDUCTIVE MATERIAL OF ORGANIC HIGH POLYMER


(57)Abstract:

PURPOSE: To provide a high polymer having high heat stability with electrical conductivity by the use of a nonpoisonous electron acceptor, by adding an electron acceptor to a polymer consisting of a poly(arylene vinylene) derivative having a carbazole skeleton in a main chain.


CONSTITUTION: An electron donor (e.g., I₂, SO₃, etc.) is added to a polymer consisting of a poly(arylene vinylene) derivative having a carbazole skeleton in a main chain shown by the formula II (R is H, or 1W16C alkyl; n is positive integer) obtained by dehydrohalogenating an N-substituted-3-vinyl-6-halocarbazole derivative shown by the formula I (R is as shown for formula II; X is Br, or I), having >2 polymerization degree, and >5, preferably >10 average polymerization degree, or shown by the formula V (R and n are as shown for formula II) obtained by reacting an N-substituted-3,6-dihalocarbazole shown by the formula III (R and X are as shown for formula I) with divinylbenzene shown by the formula IV, having >2 polymerization degree, and >5, preferably >10 average polymerization degree.



I




II



III



IV



V

LEGAL STATUS

[Date of request for examination]

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's decision of rejection]

[Date of requesting appeal against examiner's decision of rejection]

[Date of extinction of right]